



Single-Daylight Throughfeed Press Lines

Application: Upgrading of plane woodbased panels and blanks in throughfeed operation. Pressing of MDF, particleboard, thin boards etc. with veneers, finish foils, HPL, CPL etc.

Products: Furniture panels, furniture elements, flooring, parquet, interior doors, panels, worktops, sandwich components

TECHNICAL DATA	
Application	single and double-sided
Heating platen length	Up to 16,0 m
Heatingplaten width	Up 3,2 m
Carrier boards	3,2 – 50 mm
Spec. press pressure	Up to 200 N/cm ² , higher pressures possible on request
Operation mode	variable
Lay-up system	Manual or automatic
Adhesive system	PVAc-glue or urea-based glue, other systems on request
Capacity	Cycle time 25 – 90 sec.