



## Multi-Daylight Throughfeed Press Lines

**Application:** Upgrading of plane woodbased panels and blanks in throughfeed operation. Pressing of MDF, particleboard, thin boards etc. with veneers, finish foils, HPL, CPL etc.

**Products:** Furniture panels, furniture elements, flooring, parquet, interior doors, panels, worktops, sandwich components

TECHNICAL DATA	
<b>Application</b>	single and double-sided
<b>Heating platen length</b>	Up to 6,0 m, other length on request
<b>Heatingplaten width</b>	Up 2,2 m, other widths on request
<b>Carrier boards</b>	3,2 – 50 mm
<b>Spec. press pressure</b>	Up to 200 N/cm <sup>2</sup> , higher pressures possible on request
<b>Operation mode</b>	variable
<b>Lay-up system</b>	Manual or automatic
<b>Adhesive system</b>	PVAc-glue or urea-based glue, other systems on request
<b>Capacity</b>	Cycle time 60 – 600 sec.